

## AMENDMENT TO THE CLAIMS

Replace the claims with the following revised version:

1. – 14. (Canceled)

15. (Currently Amended) A cleaning method for an ALD thin film deposition equipment comprising a reactor including a reactor block on which a wafer is mounted, a wafer block installed within the reactor block, on which the wafer is seated, and a diffusion plate having a plurality of spray holes formed over the wafer block and a plurality of nozzles slanted toward the inner sidewall of the reactor block to spray a gas toward the edges of the wafer block, the cleaning method comprising:

performing a main cleaning process in a state where no wafers are received within the reactor, including spraying a mixture of a cleaning gas and an inert gas onto the wafer block through the spray holes and spraying the inert gas toward edges of the wafer block through the nozzles.

16. (Currently Amended) The cleaning method of claim 15, wherein the main cleaning process further comprises setting ~~the~~a flow rate of the cleaning gas at 50 SCCM or higher, ~~and mixing~~the inert gas mixed with the cleaning gas and flowing the mixture to the spray holes to be at 50 SCCM or higher, and setting ~~the~~a flow rate of the inert gas to the nozzles ~~to be~~ at 300 SCCM or higher.

17. (Currently Amended) The cleaning method of claim 16, further comprising setting ~~the~~an inside pressure of the reactor to be 0.5 to 10 torr.

18. (Currently Amended) The cleaning method of claim 16, further comprising setting ~~the~~an inside surface temperature of the reactor, except for the wafer block, to be 200 °C or less.

19. (Currently Amended) The cleaning method of claim 15, further comprising performing a sub cleaning process in athe state where no wafers are received within the reactor, including pulse-introducing the cleaning gas into the reactor to induce instantaneous diffusion due to a pressure fluctuation.

20. (Currently Amended) The cleaning method of claim 19, wherein the sub cleaning process further comprises setting the flow rate of the cleaning gas to be at 50 SCCM or higher, ~~setting the flow rate of~~mixing the inert gas ~~mixed~~ with the cleaning gas and flowing the mixture to the spray holes ~~to be~~ at 50 SCCM or higher, and setting ~~thea~~ flow rate of the inert gas to the nozzles ~~to be~~ at 300 SCCM or higher.

21. (Currently Amended) The cleaning method of claim 19, further comprising setting ~~thean~~ inside pressure of the reactor to be 0.5 to 10 torr.

22. (Currently Amended) The cleaning method of claim 19, further comprising setting ~~thean~~ inside surface temperature of the reactor, except for the wafer block, to be 200 °C or less.

23. (Currently Amended) The cleaning method of claim 15, further comprising performing a pre-coating process in athe state where no wafers are received within the reactor, including adhering fine particles remaining within the reactor to ~~thean~~ inside surface of the reactor.

24. (Previously Presented) The cleaning method of claim 23, wherein the pre-coating process comprises spraying a first mixture gas of a first reaction gas and the inert gas onto the wafer block through the spray holes, and spraying a second mixture gas of a second reaction gas and the inert gas toward edges of the wafer block through the nozzles.

25. (Previously Presented) The cleaning method of claim 23, wherein the pre-coating process comprises introducing a first mixture gas of a first reaction gas and the inert gas; introducing the inert gas without the first reaction gas for a predetermined period of time; introducing a second mixture gas of a second reaction gas and the inert gas into the reactor; and introducing the inert gas without the second reaction gas for a predetermined period of time.

26. (Previously Presented) The cleaning method of claim 23, wherein the pre-coating process comprises introducing a first mixture gas of a first reaction gas and the inert gas and introducing the inert gas without the first reaction gas for a predetermined period of time in a state where a second reaction gas and the inert gas are continuously introduced into the reactor.

27. (Previously Presented) The cleaning method of claim 23, wherein the pre-coating process comprises introducing  $\text{NH}_3$  gas into the reactor at least several seconds before introducing a first reaction gas into the reactor, when a compound gas containing Cl is used as the first reaction gas, and the  $\text{NH}_3$  gas is used as a second reaction gas.

28. (Original) The cleaning method of claim 15, wherein the cleaning gas is  $\text{ClF}_3$ .